

Beltech 315

Product Data Sheet

June 2014

A woven geotextile fabric, produced from polypropylene slit-film tapes, which will meet or exceed the following MARV's. This fabric is produced for use in AASHTO M-288 Class 1 and other stabilization or separation applications.

Property	Test Method	English Units			SI Units		
		MARV			MARV		
		MD	CD		MD	CD	
Grab Tensile Strength	ASTM D-4632	315	315	lbs	1402	1402	N
Grab Tensile Elongation	ASTM D-4632	20	15	%	20	15	%
Wide Width Tensile Ultimate	ASTM D-4595	200	200	lbs/in	35	35	kN/m
Wide Width Elongation	ASTM D-4595	15	15	%	15	15	%
Trapezoid Tear	ASTM D-4533	120	120	lbs	534	534	N
Puncture	ASTM D-4833	120		lbs	534		N
CBR Puncture - Typical Value	ASTM D-6241	1230		lbs	5474		N
Permittivity	ASTM D-4491	0.05		sec ¹	0.05		sec ¹¹
A.O.S.	ASTM D-4751	40		U.S. Sieve	0.425		mm
UV Resistance (500 hrs)	ASTM D-4355	80		%	80		%
Water Flow Rate	ASTM D-4491	4		gal/min/ft ²	163		l/min/m ²

Packaging	English Units			SI Units		
	Width	Area	Length	Width	Area	Length
	(feet)	(yard ²)	(yard)	(m)	(m ²)	(m)
Standard Roll Sizes	12.5	600	144	3.8	502	132
	15	600	120	4.6	502	110
	17.5	600	103	5.3	502	94

Note: Custom sizes are available. Please inquire.



Produced in Belton, South Carolina, U.S.A.

The foregoing is believed to be an accurate representation of information compiled from inside and/or outside sources, however, because test values, statistical data, and other information presented may be based solely on results of unverified tests made on random samples, information presented may relate only to tested samples and because the conditions in which such information may be used are beyond the control of Belton Industries, Inc., Belton does not guarantee either the accuracy or reliability of the information or the suggestions and recommendations contained herein. Belton assumes no responsibility for the use of information presented herein and hereby disclaims all liabilities which may arise in connection with the use of information herein presented. All specifications, properties, values, statistical data and applications listed herein are provided as information only, without charge or obligation to the recipient or user, and in no way either makes or creates any warranty with respect to any product or modifies, amends or enlarges any warranty made with respect to any product. Final determination of the suitability, reliability and accuracy of the information and suggested uses is solely the responsibility of the user. The property values expressed are effective on the date shown above, supersede any values previously published, and are subject to change without notice.

PO Box 127 · 1205 Hamby Road · Belton, South Carolina 29627

Phone 864.338.5711 / 800.845.8753 · Fax 864.338.5594 / 800.851.5049 · www.BeltonIndustries.com