



Style 1827

Product Data Sheet

December 2011

A woven geotextile fabric, produced polypropylene slit-film tapes, which meet or exceed the following MARV's.
Approved for use as a Low Velocity Cargo Chute.

Property	Test Method	English Units			SI Units		
		MARV			MARV		
		MD	CD		MD	CD	
Fabric Weight	ASTM D-5261	2.7		oz/yd ²	92		g/m ²
Grab Tensile Strength	ASTM D-4632	138	95	lbs	614	423	N
Grab Tensile Elongation	ASTM D-4632	20	15	%	20	15	%
Trapezoid Tear	ASTM D-4533	60	50	lbs	267	223	N
Air Permeability	ASTM D-737	16 - 40		ft ³ /min/ft ²	4.9 - 12.2		m ³ /min/m ²
Selvage Strength	ASTM D-5035 -2R	387	n/a	lbs	1722	n/a	N
Sevage Tear Strength	PIA 502	198	n/a	lbs	881	n/a	N

Produced in Belton, South Carolina, U.S.A.

The foregoing is believed to be an accurate representation of information compiled from inside and/or outside sources, however, because test values, statistical data, and other information presented may be based solely on results of unverified tests made on random samples, information presented may relate only to tested samples and because the conditions in which such information may be used are beyond the control of Belton Industries, Inc., Belton does not guarantee either the accuracy or reliability of the information or the suggestions and recommendations contained herein. Belton assumes no responsibility for the use of information presented herein and hereby disclaims all liabilities which may arise in connection with the use of information herein presented. All specifications, properties, values, statistical data and applications listed herein are provided as information only, without charge or obligation to the recipient or user, and in no way either makes or creates any warranty with respect to any product or modifies, amends or enlarges any warranty made with respect to any product. Final determination of the suitability, reliability and accuracy of the information and suggested uses is solely the responsibility of the user. The property values expressed are effective on the date shown above, supersede any values previously published, and are subject to change without notice.