

Style 1841

Product Data Sheet February 2016

A woven agricultural fabric, produced from polypropylene slit-film tapes, which meet or exceed the following:

Property	Test Method	English Units			SI Units		
		Typical Values			Typical Values		
		MD	CD		MD	CD	
Mass per Unit Area	ASTM D-5261	3.1		oz/yd ²	105		g/m ²
Grab Tensile Strength	ASTM D-4632	150	115	lbs	668	512	N
Grab Tensile Elongation	ASTM D-4632	18	16	%	18	16	%
Air Permeability	ASTM D-737	33.5		ft ³ /min/ft ²	10.2		m ³ /min/m ²
UV Resistance (2000 hrs) *	ASTM D-4355	85		%	85		%

*Note: Exposure of this product to certain agrochemicals may have an adverse affect on the service life of the fabric. Some agrochemicals contain in their structure active halogens (such as chlorine) and sulphur, or other byproducts which reduce the service life of woven polypropylene fabrics. Accelerated polymer degradation and/or photodegradation may occur. Please consult your agrochemical supplier for information and other available options.



Produced in Belton, South Carolina, U.S.A.

The foregoing is believed to be an accurate representation of information complied from inside and/or outside sources, however, because test values, statistical data, and other information presented may be based solely on results of unverified tests made on random samples, information presented may relate only to tested samples and because the conditions in which such information may be used are beyond the control of Belton Industries, Inc., Belton does not guarantee either the accuracy or reliability of the information or the suggestions and recommendations contained herein. Belton assumes no responsibility for the use of information presented herein and hereby disclaims all liabilities which may arise in connection with the use of information herein presented. All specifications, properties, values, statistical data and applications listed herein are provided as information only, without charge or obligation to the recipient or user, and in no way either makes or creates any warranty with respect to any product or modifies, amends or enlarges any warranty made with respect to any product. Final determination of the suitability, reliability and accuracy of the information and suggested uses is solely the responsibility of the user.