



Style 1524

Product Data Sheet

January 2014

A woven fabric, produced from polypropylene slit-film tapes, which will meet or exceed the following specifications.

Property	Test Method	English Units			SI Units		
		Typical Value			Typical Value		
		MD	CD		MD	CD	
Mass per Unit Area	ASTM D-5261	4.8		oz/yd ²	163		g/m ²
Fabric Count	ASTM D-3775	24	18	yarns/inch	9.4	7.1	yarns/cm
Grab Tensile Strength	ASTM D-4632	265	245	lbs	1179	1090	N
Grab Tensile Elongation	ASTM D-4632	24	24	%	20	24	%
Pin Ravel - Heat Slit Edge	ASTM D-751	na	110	lbs	na	490	N
Pin Ravel - Cold Cut Edge	ASTM D-751	na	85	lbs	na	378	N
Mullen Burst	ASTM D-3786	460		lb/in ²	3172		kPa

Produced in Belton, South Carolina, U.S.A.

The foregoing is believed to be an accurate representation of information compiled from inside and/or outside sources, however, because test values, statistical data, and other information presented may be based solely on results of unverified tests made on random samples, information presented may relate only to tested samples and because the conditions in which such information may be used are beyond the control of Belton Industries, Inc., Belton does not guarantee either the accuracy or reliability of the information or the suggestions and recommendations contained herein. Belton assumes no responsibility for the use of information presented herein and hereby disclaims all liabilities which may arise in connection with the use of information herein presented. All specifications, properties, values, statistical data and applications listed herein are provided as information only, without charge or obligation to the recipient or user, and in no way either makes or creates any warranty with respect to any product or modifies, amends or enlarges any warranty made with respect to any product. Final determination of the suitability, reliability and accuracy of the information and suggested uses is solely the responsibility of the user.