

Style 1765

Product Data Sheet September 2014

A woven fabric, produced from polypropylene slit-film tapes, which will meet or exceed the following specifications.

Property	Test Method	English Units			SI Units		
		Typical Value			Typical Value		
Mass per Unit Area	ASTM D-5261	5.0		oz/yd ²	170		g/m ²
Fabric Count	ASTM D-3775 *	24	15	yarns/inch	9.4	5.9	yarns/cm
Grab Tensile Strength	ASTM D-4632	345	250	lbs	1535	1113	N
Grab Tensile Elongation	ASTM D-4632	25.5	18.8	%	20.0	18.8	%
Mullen Burst	ASTM D-3786 *	565		lb/in ²	3896		kPa

* Note: This method is not within the scope of our A2LA Accreditation



Produced in Belton, South Carolina, U.S.A.

The foregoing is believed to be an accurate representation of information compiled from inside and/or outside sources, however, because test values, statistical data, and other information presented may be based solely on results of unverified tests made on random samples, information presented may relate only to tested samples and because the conditions in which such information may be used are beyond the control of Belton Industries, Inc., Belton does not guarantee either the accuracy or reliability of the information or the suggestions and recommendations contained herein. Belton assumes no responsibility for the use of information presented herein and hereby disclaims all liabilities which may arise in connection with the use of information herein presented. All specifications, properties, values, statistical data and applications listed herein are provided as information only, without charge or obligation to the recipient or user, and in no way either makes or creates any warranty with respect to any product or modifies, amends or enlarges any warranty made with respect to any product. Final determination of the suitability, reliability and accuracy of the information and suggested uses is solely the responsibility of the user. The property values expressed are effective on the date shown above, supersede any values previously published, and are subject to change without notice.

PO Box 127 · 1205 Hamby Road · Belton, South Carolina 29627

Phone 864.338.5711 / 800.845.8753 · Fax 864.338.5594 / 800.851.5049 · www.BeltonIndustries.com