



Style 5018

Provisional Data Sheet

April 2015

A woven narrow fabric, produced from polypropylene slit-film tapes, which meet or exceed the following values. This fabric contains UV stabilizer.

Property	Test Method	English Units		SI Units	
		Typical Values		Typical Values	
Fabric Width	ASTM D-3774	3.7	inches	94	mm
Fabric Weight	ASTM D-5261	1.6	oz/yd	50	g/m
Fabric Weight	ASTM D-5261	15.7	oz/yd ²	532	g/m ²
Tensile Strength	ASTM D-6775, modified *	3300	lbs	15	kN
Elongation	ASTM D-6775, modified *	25	%	25	%
Elongation @ 750 lbs Load	ASTM D-6775, modified *	5.0	%	5	%

* ASTM D-6775 is performed using hydraulic grips rather than prescribed split drum grips, and is not within or scope of accreditation.

Produced in Belton, South Carolina, U.S.A.

The foregoing is believed to be an accurate representation of information compiled from inside and/or outside sources, however, because test values, statistical data, and other information presented may be based solely on results of unverified tests made on random samples, information presented may relate only to tested samples and because the conditions in which such information may be used are beyond the control of Belton Industries, Inc., Belton does not guarantee either the accuracy or reliability of the information or the suggestions and recommendations contained herein. Belton assumes no responsibility for the use of information presented herein and hereby disclaims all liabilities which may arise in connection with the use of information herein presented. All specifications, properties, values, statistical data and applications listed herein are provided as information only, without charge or obligation to the recipient or user, and in no way either makes or creates any warranty with respect to any product or modifies, amends or enlarges any warranty made with respect to any product. Final determination of the suitability, reliability and accuracy of the information and suggested uses is solely the responsibility of the user. The property values expressed are effective on the date shown above, supersede any values previously published, and are subject to change without notice.

PO Box 127 · 1205 Hamby Road · Belton, South Carolina 29627

Phone 864.338.5711 / 800.845.8753 · Fax 864.338.5594 / 800.851.5049 · www.BeltonIndustries.com